

CartonMate® C2S-LC Bleached Board

Reliability. It's that simple.®

Qualities:

- Smooth, bright appearance for excellent printability
- Light backside coating for barrier and sealing performance
- Consistent roll-to-roll quality
- FDA-compliant for contact with most dry, fatty and aqueous foods

Typical Properties

Caliper	.014	.015	.016	.017	.018	.020	.022	.024
Nominal Basis Weight	56.5	59.5	62.5	66.5	68.5	74.5	80.5	85.5
Apparent Density	12.11	11.90	11.72	11.74	11.42	11.18	10.84	10.69
Taber Stiffness								
MD	130	155	180	210	245	315	395	495
CD	60	70	80	95	110	145	185	230
GM	88	104	120	141	164	214	270	337
GE Brightness	86	86	86	86	86	86	86	86
Color Hunter b Value	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
Sheffield Smoothness	20	22	24	26	28	32	36	40
ZDT	44	42	42	40	40	39	39	38
Percent Moisture	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0

The information provided here identifies the target value for each product. The actual value of the characteristics may vary slightly from one run to another. This information is subject to change without notice.

CartonMate C2S-LC Bleached Board is produced at our Demopolis Mill in Demopolis, AL.

Contact Us:
www.rocktenn.com
877.643.5414



*Good for you.
Good for our forests.™*