

Uncoated Millennium® Recycled Board

Reliability. It's that simple.®

Qualities:

- 100% recycled fiber with an average of 35% post-consumer content
- 2:1 stiffness ratio and high strength characteristics
- Clean, brown surface with smooth top side suitable for multi-color printing
- FDA-compliant for contact with most dry, fatty and aqueous foods

Typical Properties

Caliper	.016	.018	.020	.022	.024	.026	.028	.030	.032	.034
Nominal Basis Weight	65	72	80	85	90	96	103	111	115	124
Taber Stiffness										
MD	165	220	280	350	465	570	670	730	810	930
CD	80	115	135	175	225	260	305	355	395	440
Tear										
MD	375	490	450	520	570	620	700	720	770	820
CD	440	465	490	560	600	650	730	780	830	884

The information provided here identifies the target value for each product. The actual value of the characteristics may vary slightly from one run to another. This information is subject to change without notice.

Uncoated Millennium Recycled Board is produced at our Stroudsburg Mill in Delaware Water Gap, PA.



Contact Us:

www.rocktenn.com
877.643.5414